

POLISHING PAD

SPECIFICATION FOR THE 1ST AND 2ST POLISHING

TYPE	Suba400	Suba400H	Suba600	Suba800	MH S15A	MH S24A
STEP	2 ND	2 ND	1 ST	1 ST	1 ST	1 ST
THICKNESS(mm)	1.27	1.27	1.27	1.27	1	1
DENSITY(g/cm ²)	–	–	–	–	0.53	0.4
HARDNESS(Asker,	61	68	80	82	–	–
HARDNESS(JIS,A)	–	–	–	–	85	80
CONDENSATION(8	6	3.5	3	3	3.5
ELASTICITY(%)	88	86	75	73	–	–

SPECIFICATION FOR FINAL POLISHING

TYPE	Supreme	Supreme	UR 100	#750
THICKNESS(mm)	1.5	1.5	1.5	1.3
CONDENSATION(11	13	14	15

